



TEST REPORT

DATE: 01-18-2016

TEST NUMBER: 0225144

CLIENT	Metroflor Corp.
---------------	-----------------

TEST METHOD CONDUCTED	Standing Liquid Seam Test
------------------------------	---------------------------



DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	Engage Genesis 2000 (C1) Also Applies to: Engage Genesis 1200 (C1)
REFERENCE	MET0288

GENERAL PRINCIPLE

The submitted locking planks were assembled to have an end joint and two edges in order to form a "T" joint. A 9mm deep pool of liquid was held over T joint by 6" diameter PVC ring sealed to sample with sealing compound. The volume of liquid used was 200ml. The sample was held under the applied liquid for 24 hrs. Visual evaluation and swell measurement were performed initially and after conclusion of test. The thickness was measured by compressometer over 6 marked areas of the seam. The material was also examined for any color change and rated by the AATCC Grey Scale. This test was conducted using cat urine at the client's request.

TEST RESULTS

	Position 1	Position 2	Position 3	Position 4	Position 5	Position 6
Swell	0.00 mm	0.00 mm	0.00 mm	0.00 mm	0.00 mm	0.00 mm

No penetration occurred through the seam. There was no color change noted, 5.0 grey scale rating.

APPROVED BY:

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.